Technical Data Sheet TUFF Shield Mouldings Paint (MP)



(previously known as Impact Paint)

USES

- TUFF Render
- TUFFmouldings
- TUFFTEX texture range
- Traditional sand finish plaster
- Painted brickwork
- Concrete walls

NB.

TUFF Shield TP was previously known as Protective Top Coat (PTC).

TUFF Shield MP was previously known as Impact paint.

TUFF Shield MP is a high performance surface coating with a satin (low sheen) gloss level that can be factory tinted to your choice of colour. A minimum of two coats are recommended for maximum coverage. This film build offers protection against the effects of weather (rain, temperature extremes, solar radiation and wind effects, etc.). TUFF Shield MP can be brushed or roller coated over textured walls, mouldings and profiles.

- 10 Year Warranty
- Water Based
- Durable flexible acrylic
- Excellent colour retention
- Supports adhesion & extends durability of textured coatings
- Ensures consistent appearance and finish of total system.
- Resists pollution, chemical attack and dirt pick-up.
- Easy, safe and economical clean-up
- Resists attack from bacteria and fungi.

Substrate condition:

All substrate surfaces must be clean sound, dry, cured and free of any dust, dirt mould, fungus, grease or other contaminates. Any loose or damaged substrate must be removed, or patched & repaired and any moisture must also evaporate out prior to TUFF Shield MP being applied onto the substrate. All surfaces must be clear of efflorescence, grease, oil, mould, dirt, dust, release agents, bond-breakers or other contaminants that may interfere with adhesion. Pre-painted surfaces must be wire brushed or high pressure water blasted to remove loose and cracking paint.

Application:

Brush, Nap Roller or Spray

Sizes: 15Ltr Bucket

Weather Conditions:

If temperatures are less than 8 °C or greater than 30°C, TUFF Shield MP is not recommended to be applied to the substrate.

Freshly applied TUFF Shield MP must be protected from rain, other sources of moisture and frosts for at least 48 hours.

TUFF Shield MP

- Coverage Approximately 50-60m²
- Wet Film Thickness 250 microns (approx)
- Dry Film Thickness 125 microns (approx)
- Shelf Life 12-24 months is to be expected.
- Product Safety See MSDS

TUFF Shield MP membrane is classified as non-hazardous according to the criteria of NOHSC. Not classified as dangerous goods according to the Australian Code for Transport of Dangerous Goods. NON DANGEROUS GOODS

